

AMENDMENTS TO THE CLAIMS

List of Claims

1. (Currently Amended) A meltable ink which is solid at room temperature and liquid at a higher temperature, which ink is suitable for use in an indirect printing process, in which printing process the ink is transferred, by the use of an inkjet printhead, in the form of individual ink drops to a transfer element, whereafter the ink is transferred to a receiving material by bringing the transfer element into contact with said receiving material under pressure, said ink having a composition such that it is pressure-transferable at a temperature between a bottom temperature limit and a top temperature limit, wherein the ink has a deformation energy of less than 20×10^5 Pa.s at a temperature equal to the top temperature limit.

2. (Original) A meltable ink according to claim 1, wherein the ink has a deformation energy less than 10×10^5 Pa.s at a temperature equal to the top limit.

3. (Original) A meltable ink according to claim 2, wherein the ink has a deformation energy smaller than 2×10^5 Pa.s at a temperature equal to the top limit.

4. (Original) A meltable ink according to claim 1, 2 or 3, wherein the ink contains a semi-crystalline binder and a crystalline thickener.

5. (Original) A meltable ink according to claim 1, 2 or 3, wherein the ink contains a binder, an amorphously solidifying softener and a crystalline thickener.

6. (Original) A meltable ink according to claim 1, 2 or 3, wherein the ink contains a crystalline-solidifying softener, a crystalline thickener and optionally a binder.

7. (Currently Amended) A method of selecting a meltable ink which is solid at room temperature, suitable for use in an indirect printing process, in which printing process the ink is transferred, by the use of an inkjet printhead, to a transfer element, whereafter the ink is transferred under pressure from the transfer element to a receiving material, which ink has a composition such that said ink is pressure-transferable at a temperature between a bottom temperature limit and a top temperature limit, the method comprising:

- determining whether the ink is pressure-transferable,
- determining the top ~~limit~~ if temperature limit at which the ink is pressure-transferable,

~~wherein the method further comprises:~~

- measuring the deformation energy of the ink at the said top temperature limit, and

- selecting the ink if the deformation energy is less than 20×10^5

Pa.s.

8. (Currently Amended) ~~A method~~ The method according to claim 7, wherein the ink is selected if the deformation energy is less than 10×10^5 Pa.s.

9. (Currently Amended) ~~A method~~ The method according to ~~claim 8,~~ claim 7, wherein the ink is selected if the deformation energy is less than 2×10^5 Pa.s.